



Reliance Industries Limited

P O L Y P R O P Y L E N E

REPOL H110FG

Provisional Technical Data Sheet

Repol H110FG is recommended for Staple Fibres & Continuous High Tenacity Filaments. The grade is specially formulated for Anti gas fading stability. Repol H110FG is an ideal material for spinning of fine denier staple fibres.

Typical Characteristics			
Property	Test Method	Unit	Typical Value *
Melt Flow Rate, (230°C / 2.16kg)	ASTM D1238	g/10min	9.0
Tensile Strength at Yield (50mm/min)	ASTM D638	MPa	35
Elongation at Yield (50mm/min)	ASTM D638	%	8
Flexural Modulus (1% secant)	ASTM D790A	MPa	1600
Notched Izod Impact strength (23°C)	ASTM D256	J/m	30
Heat Deflection Temperature (455 kPa)	ASTM D648	°C	104

* Typical values, not to be taken as specification.

* Tensile properties as per ASTM D638 Type-I specimen injection molded and tested in accordance with ASTM D 4101

Applications : Staple fibres for thermal bonded & needle punched nonwovens; High tenacity filament yarns.

Regulatory Information: Meets the requirements stipulated in IS 10910 on “Specification for Polypropylene and its copolymers for safe use in contact with foodstuffs, pharmaceuticals, and drinking water”. Additives incorporated in this grade conform to the positive list of constituents as prescribed in IS 10909. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177.1520, Olefin polymers.

Storage Recommendations : Bags should be stored in dry conditions at temperatures below 50°C and protected from UV / direct sunlight

The data, information and suggestions contained herein are given purely as a guide. Reliance Industries Limited and Reliance Group Companies undertake no responsibility either for the results deriving from their adoption or for possible positions in apparent contrast with existing patent rights