



Reliance Industries Limited

P O L Y P R O P Y L E N E	
REPOL SS80N	HOMOPOLYMER FOR CAST PP FILMS
<i>Provisional Technical Data Sheet</i>	

Repol SS80N is recommended for use in Cast Film application, specially designed for use as a core layer in coextruded cast film applications. Repol SS80N is an ideal material for food and general purpose packaging. Grade does not contain slip and antiblock additives.

Typical Characteristics			
Property	Test Method	Unit	Typical Value *
Melt Flow Rate, (230°C / 2.16kg)	ASTM D1238	g/10min	7.0
Tensile strength at Yield (50mm/min)	ASTM D638	MPa	36
Elongation at Yield (50mm/min)	ASTM D638	%	11
Flexural Modulus (1% secant)	ASTM D790A	MPa	1450
Notched Izod Impact strength (23°C)	ASTM D256	J/m	30
Heat Deflection Temperature (455 kPa)	ASTM D648	°C	105

* Typical values, not to be taken as specification.

* All the mechanical properties as per ASTM D638 Type I specimen injection moulded and tested with accordance with ASTM D 4101

Application :

- Food packaging film, Lamination Film, Confectionary films & other general purpose packaging.

Regulatory Information

- Meets the requirements stipulated in IS 10910 on “Specification for Polypropylene and its copolymers for safe use in contact with foodstuffs, pharmaceuticals, and drinking water”. Additives incorporated in this grade conform to the positive list of constituents as prescribed in IS 10909. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177.1520, Olefin polymers.

Storage Recommendations

- Bags should be stored in dry conditions at temperatures below 50°C and protected from UV / direct sunlight