

Product: Semi Dull POY

Nominal Denier	No. of Filaments	Colour	Lustre	Cross-section	Package Size (kgs)	Suggested Draw Ratio	Resultant Dry Denier	Comments
51	14	Raw White	Semi-Dull	Round	15-18	1.75	32	
75	34/36	Raw White	Semi-Dull	Round	18	1.75	48	
100	34/36	Raw White	Semi-Dull	Round	15-18	1.73	60	
100	34/36	Raw White	Semi-Dull	Round	15	1.69	60	
115	36	Raw White	Semi-Dull	Round	16	1.72	72.0	
115	48	Raw White	Semi-Dull	Round	16	1.711	72.0	
126	34	Raw White	Semi-Dull	Round	18	1.75	77	For short heater
130	72	Raw White	Semi-Dull	Round	16	1.65	75.8	
135	34/36	Raw White	Semi-Dull	Round	18	1.73	79	
135	48	Raw White	Semi-Dull	Round	16	1.711	77.5	
130	34	Raw White	Semi-Dull	Round	18	1.73	79	
155	34	Raw White	Semi-Dull	Round	18	1.74	96	
235	34	Raw White	Semi-Dull	Octolobal	18	1.64	148	
235	34	Raw White	Semi-Dull	Round	18	1.64	148	
235	48	Raw White	Semi-Dull	Round	18	1.65	146	
260	36	Raw White	Semi-Dull	Round	16	1.70	152.0	
265	34	Raw White	Semi-Dull	Round	18	1.64	158	
250	34	Raw White	Semi-Dull	Round	15	1.69	156	For short heater
250	34	Raw White	Semi-Dull	Round	18	1.74	155	
250	48	Raw	Semi-	Round	18	1.74	155	For short

		White	Dull					heater
250	48	Raw White	Semi-Dull	Round	18	1.64	164	
470	68	Raw White	Semi-Dull	Round	18	1.6	305	
500	68-72	Raw White	Semi-Dull	Round	18	1.62	315	
80	24	Raw White	Semi-Dull CD	Round	15	1.711	52.0	
130	36	Raw White	Semi-Dull CD	Round	15	1.711	80.0	
130	72	Raw White	Semi-Dull CD	Round	15	1.62	83	
115	96	Raw White	Semi-Dull	Round	15	1.62	75	
115	108	Raw White	Semi-Dull	Round	18	1.62	78	
115	108	Raw White	Semi-Dull	Round	18	1.61	75	For short heater
115	108	Raw White	Semi-Dull	Round	18	1.62	78	
115	120	Raw White	Semi-Dull	Round	15	1.62	75	
130	96	Raw White	Semi-Dull	Round	14.5	1.55	80	
155	108	Raw White	Semi-Dull	Round	18	1.66	99	
160	156	Raw White	Semi-Dull	Round	15	1.62	103	
250	108	Raw White	Semi-Dull	Round	18	1.66	156	
250	108	Raw White	Semi-Dull	Round	18	1.66	157	