

Property	Recron [®] 3S
Denier d	1.5
Cut length mm	4.5, 6, 9, 12 Straight and crimped
Tenacity gpd	~ 5
Elongation%	~ 45-65
Specific gravity	1.36
Dispersion in water	Excellent
Acid resistance	Excellent
Resistance to organic solvents	Excellent



Reliance