

15.0 DENIER HOLLOW RECRON® POLYESTER FIBRE FILL VARIANTS

Nominal Denier	15
Type	Hollow
Finish	Non-Siliconised
Denier Range	15.0 ±1.0
Crimps per Cm	2.0 ±0.5
% Finish - Avg.	0.15
% Silicon - Avg.	-
% DHS at 180°C	< 3.0
Cross Section	Circular with single Hollow

Note: None of the above variants are Fire Retardant.



Reliance