

6.0 DENIER HOLLOW RECRON® POLYESTER FIBRE FILL VARIANTS

Nominal Denier 6	
Type	Hollow
Finish	Slick
Denier Range	6.0± 0.3
Crimps per Cm	2.5± 0.5
% Finish - Avg.	0.27
% Silicon - Avg.	-
% DHS at 180°C	< 3.0
Cross Section	Circular with single Hollow

Note: None of the above variants are Fire Retardant.



Reliance