

1.4 D, Circular Bright

Specification Sheet No.: PSF-11

Revision No.: 0

Date of issue : 01-03-2004

Grade : FIRST

Nominal Denier	1.4
Denier	1.31 \pm 0.05
Tenacity, gpd	6.6 \pm 0.4
Elongation, %	26.0 \pm 5.0
Crimps/cm	3.6 - 4.3
DHS at 196° C - 30 minutes, %	Max 9.0
Finish, %	0.145 \pm 0.015

- Denier tested on Vibromat-ME
- Tensiles tested on Fafegraph-HR at 10 mm guage length.



Reliance