

3.0 D, Circular Brightt

Specification Sheet No.: PSF-13

Revision No.: 0

Date of issue : 01-03-2004

Grade : FIRST

Nominal Denier	3.0
Denier	2.70 \pm 0.07
Tenacity, gpd	5.8 \pm 0.5
Elongation, %	36.0 \pm 6.0
Crimps/cm	3.4 - 4.0
DHS at 196° C - 30 minutes, %	Max 9.0
Finish, %	0.180 \pm 0.015

- Denier tested on Vibromat-ME
- Tensiles tested on Fafegraph-HR at 10 mm guage length.



Reliance