

2.5 D, Circular Bright Medium Tenacity

Specification Sheet No.: PSF-19

Revision No.: 0

Date of issue : 01-03-2004

Grade : FIRST

Nominal Denier	2.5 (MT)
Denier	2.25 \pm 0.08
Tenacity, gpd	4.5 \pm 0.5
Elongation, %	65 \pm 10
Crimps/cm	3.4 - 4.1
DHS at 196° C - 30 minutes, %	Max 9.0
Finish, %	0.200 \pm 0.015

- Denier tested on Vibromat-ME
- Tensiles tested on Fafegraph-HR at 10 mm guage length.



Reliance