

1.2 D, Circular Bright Super High Tenacity

Specification Sheet No.: PSF-14

Revision No.: 0

Date of issue : 01-03-2004

Grade : FIRST

Nominal Denier	1.2 (SHT)
Denier	1.16 \pm 0.05
Tenacity, gpd	7.5 \pm 0.4
Elongation, %	19 \pm 5
Crimps/cm	3.6 - 4.4
DHS at 196° C - 30 minutes, %	Max 5.0
Finish, %	0.145 \pm 0.015

- Denier tested on Vibromat-ME
- Tensiles tested on Fafegraph-HR at 10 mm guage length.



Reliance