

1.4 D, Circular Semi-Dull

Specification Sheet No.: PSF-4

Revision No.: 0

Date of issue : 01-03-2004

Grade : FIRST

Nominal Denier	1.4
Denier	1.37 \pm 0.05
Tenacity, gpd	6.4 \pm 0.4
Elongation, %	24 \pm 5
Crimps/cm	3.6 - 4.2
DHS at 196° C - 30 minutes, %	Max 6.5
Finish, %	0.145 \pm 0.015

- Denier tested on Vibromat-ME
- Tensiles tested on Fafegraph HR at 10 mm guage length.



Reliance