

3.0 D, Circular Semi-Dull

Specification Sheet No.: PSF-6

Revision No.: 0

Date of issue : 01-03-2004

Grade : FIRST

Nominal Denier	3.0
Denier	2.85± 0.08
Tenacity, gpd	6.2 ±0.4
Elongation, %	17 ±5
Crimps/cm	3.0 - 3.5
DHS at 196° C - 30 minutes, %	Max 9.0
Finish, %	0.180 ±0.015

- Tensiles tested on Instron at 10 inches guage length.
- Dry Heat Shrinkage on annealed tow.



Reliance