

3.0 D, Circular Semi-Dull No Dye Guarantee

Specification Sheet No.: PSF-7

Revision No.: 0

Date of issue : 01-03-2004

Grade : FIRST

Nominal Denier	3.0
Denier	3.00 ±0.08
Tenacity, gpd	5.3 ±0.5
Elongation, %	46 ±8.0
Crimps/cm	3.2 - 3.8
DHS at 196° C - 30 minutes, %	Max 9.0
Finish, %	0.180 ±0.015

- Denier Tested on Vibromat ME
- Tensiles tested on Fafegraph-HR at 10 mm guage length.



Reliance