

2.5 D, Low Tenacity Circular Tow

Specification Sheet No.: PT-2

Revision No.: 0

Date of issue : 01-03-200

Grade : FIRST

Nominal Denier	2.5 (LT)
Denier	2.45± 0.08
Tenacity, gpd	3.6± 0.5
Elongation, %	65 ±10
Crimps/cm	3.4 - 4.1
DHS at 196° C - 30 minutes, %	Max 8.0
Finish, %	0.200 ±0.015

- Denier tested on Vibromat-ME
- Tensiles tested on Fafegraph HR at 10 mm guage length



Reliance