

## **2.5 D - OW Circular Optically Whitened (HST)**

Specification Sheet No.: PSF-23

Revision No.: 0

Date of issue : 01-03-2004

Grade : FIRST

Nominal Denier	1.2 (MT)
Denier	1.16 $\pm$ 0.05
Tenacity, gpd	7.5 $\pm$ 0.4
Elongation, %	20 $\pm$ 5
Crimps/cm	3.6 - 4.4
DHS at 196° C - 30 minutes, %	Max 5.0
Finish, %	0.145 $\pm$ 0.015

- Denier tested on Vibromat-ME
- Tensiles tested on Fafegraph-HR at 10 mm guage length.



Reliance