

1.5 D, Trilobal Bright

Specification Sheet No.: PSF-16

Revision No.: 0

Date of issue : 01-03-2004

Grade : FIRST

Nominal Denier	1.5
Denier	1.65 \pm 0.07
Tenacity, gpd	5.8 \pm 0.5
Elongation, %	30 \pm 5
Crimps/cm	3.6 - 4.4
DHS at 196° C - 30 minutes, %	Max 9.0
Finish, %	0.180 \pm 0.015

- Denier tested on Vibromat-ME
- Tensiles tested on Fafegraph-HR at 10 mm guage length.



Reliance